

From the INTERNATIONAL BUREAU

PCT**NOTIFICATION OF ELECTION**

(PCT Rule 61.2)

To:

Assistant Commissioner for Patents
 United States Patent and Trademark
 Office
 Box PCT
 Washington, D.C.20231
 ETATS-UNIS D'AMERIQUE

in its capacity as elected Office

Date of mailing (day/month/year) 30 August 2000 (30.08.00)	
International application No. PCT/EP00/00357	Applicant's or agent's file reference 95.0114
International filing date (day/month/year) 13 January 2000 (13.01.00)	Priority date (day/month/year) 16 January 1999 (16.01.99)
Applicant SAWDON, Christopher et al	

1. The designated Office is hereby notified of its election made:



in the demand filed with the International Preliminary Examining Authority on:

31 July 2000 (31.07.00)



in a notice effecting later election filed with the International Bureau on:

2. The election ☒ was

was not

made before the expiration of 19 months from the priority date or, where Rule 32 applies, within the time limit under Rule 32.2(b).

The International Bureau of WIPO
 34, chemin des Colombettes
 1211 Geneva 20, Switzerland

Facsimile No.: (41-22) 740.14.35

Authorized officer

Zakaria EL KHODARY

Telephone No.: (41-22) 338.83.38

PCT

INTERNATIONAL PRELIMINARY EXAMINATION REPORT

(PCT Article 36 and Rule 70)

Applicant's or agent's file reference WO 95.0114	FOR FURTHER ACTION		See Notification of Transmittal of International Preliminary Examination Report (Form PCT/IPEA/416)
International application No. PCT/EP00/00357	International filing date (day/month/year) 13/01/2000	Priority date (day/month/year) 16/01/1999	
International Patent Classification (IPC) or national classification and IPC C09K7/06			
Applicant SOFITECH N.V. et al.			

1. This international preliminary examination report has been prepared by this International Preliminary Examining Authority and is transmitted to the applicant according to Article 36.



2. This REPORT consists of a total of 6 sheets, including this cover sheet.

- ☐ This report is also accompanied by ANNEXES, i.e. sheets of the description, claims and/or drawings which have been amended and are the basis for this report and/or sheets containing rectifications made before this Authority (see Rule 70.16 and Section 607 of the Administrative Instructions under the PCT).

These annexes consist of a total of sheets.

3. This report contains indications relating to the following items:

- I ☒ Basis of the report
- II ☐ Priority
- III ☐ Non-establishment of opinion with regard to novelty, inventive step and industrial applicability
- IV ☐ Lack of unity of invention
- V ☒ Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement
- VI ☒ Certain documents cited
- VII ☐ Certain defects in the international application
- VIII ☒ Certain observations on the international application

Date of submission of the demand 31/07/2000	Date of completion of this report 19.01.2001
Name and mailing address of the international preliminary examining authority:  European Patent Office D-80298 Munich Tel. +49 89 2399 - 0 Tx: 523656 epmu d Fax: +49 89 2399 - 4465	Authorized officer olde Scheper, B Telephone No. +49 89 2399 2141 

**INTERNATIONAL PRELIMINARY
EXAMINATION REPORT**

International application No. PCT/EP00/00357

I. Basis of the report

1. This report has been drawn on the basis of *(substitute sheets which have been furnished to the receiving Office in response to an invitation under Article 14 are referred to in this report as "originally filed" and are not annexed to the report since they do not contain amendments (Rules 70.16 and 70.17).):*

Description, pages:

1-8 as originally filed

Claims, No.:

1-11 as originally filed

2. With regard to the **language**, all the elements marked above were available or furnished to this Authority in the language in which the international application was filed, unless otherwise indicated under this item.

These elements were available or furnished to this Authority in the following language: , which is:

- ☐ the language of a translation furnished for the purposes of the international search (under Rule 23.1(b)).
☐ the language of publication of the international application (under Rule 48.3(b)).
☐ the language of a translation furnished for the purposes of international preliminary examination (under Rule 55.2 and/or 55.3).

3. With regard to any **nucleotide and/or amino acid sequence** disclosed in the international application, the international preliminary examination was carried out on the basis of the sequence listing:

- ☐ contained in the international application in written form.
☐ filed together with the international application in computer readable form.
☐ furnished subsequently to this Authority in written form.
☐ furnished subsequently to this Authority in computer readable form.
☐ The statement that the subsequently furnished written sequence listing does not go beyond the disclosure in the international application as filed has been furnished.
☐ The statement that the information recorded in computer readable form is identical to the written sequence listing has been furnished.

4. The amendments have resulted in the cancellation of:

- ☐ the description, pages:
☐ the claims, Nos.:
☐ the drawings, sheets:

5. ☐ This report has been established as if (some of) the amendments had not been made, since they have been considered to go beyond the disclosure as filed (Rule 70.2(c)):

**INTERNATIONAL PRELIMINARY
EXAMINATION REPORT**

International application No. PCT/EP00/00357

(Any replacement sheet containing such amendments must be referred to under item 1 and annexed to this report.)

6. Additional observations, if necessary:

V. Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement

1. Statement

Novelty (N)	Yes:	Claims	2,5,7-9
	No:	Claims	1,3,4,6,10,11
Inventive step (IS)	Yes:	Claims	
	No:	Claims	1-11
Industrial applicability (IA)	Yes:	Claims	1-11
	No:	Claims	

2. Citations and explanations
see separate sheet

VI. Certain documents cited

1. Certain published documents (Rule 70.10)

and / or

2. Non-written disclosures (Rule 70.9)

see separate sheet

VIII. Certain observations on the international application

The following observations on the clarity of the claims, description, and drawings or on the question whether the claims are fully supported by the description, are made:

see separate sheet

Re Item V

Reasoned statement under Rule 66.2(a)(ii) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement

Reference is made to the following documents:

- D1: Calloni, G. et al; "Carbon Black, A Low Cost Colloidal Additive for Controlling Gas-Migration in Cement Slurries"; SPE International Symposium on Oilfield Chemistry; San Antonio, Texas, USA; 14-17 February 1995; SPE 28959; XP-000915655
- D2: US-A-4 012 329
- D3: US-A-4 689 161
- D4: EP-A-0 449 257
- D5: Encyclopedia of Polymer Science and Engineering; Mark, H.F. et al, editors; John Wiley & Sons, New York; Vol. 2, "Carbon Black", pages 623-637

1. The present application relates to a electrically conductive invert emulsion wellbore fluid (claims 1-9), a method for drilling or completing a well (claim 10), and a method of providing enhanced information (claim 11).
2. D1 discloses an invert emulsion comprising carbon black and a surfactant (see page 146, 2nd column, 5th paragraph; page 148 "Field Application"; Tables 1-2, slurry "D" and "E". Although no "HLB" values are indicated it is reasonable to assume that said value is below 12.
3. D2 discloses the same wellbore fluids as the present applications, but does not cite carbon black particles. It is however indicated that further additives may be added (column 5, lines 24-35).
4. D3 discloses tendrillar carbonaceous material (TCM) and carbon black as additives (viscosifiers) for invert drilling fluids. The TCM particle dimensions are comparable with those of carbon black (see column 1, lines 42-55; column 10, line 19 to column 11, line 36; Examples 10, 11, 14; Tables 5, 6, 8-10; Figure 1)
5. D4 teaches that carbon black is an usual additive for invert drilling muds (page 4,

**INTERNATIONAL PRELIMINARY
EXAMINATION REPORT - SEPARATE SHEET**

International application No. PCT/EP00/00357

lines 13-15).

6. D5 discloses the definition of carbon blacks.
7. Thus, the subject-matter of present claims 1, 3, 4, 6, 10, and 11 lacks novelty in view of the cited prior art (Art. 33(2) PCT).
8. Even if novelty would be established it remains questionable whether the application involves an inventive step in accordance with Art. 33(3) PCT. Carbon black is an additive which is known in the art as a viscosifier or gas-block additive (D1, D3, D4). Carbon black is also known to impart electrical conductivity to substances (D5, page 633, 3rd paragraph).
If document D2 is taken as closest prior art then the objective problem in view of said document would be to provide a further embodiment of the compositions of D2. Adding a known additive in order to provide a further embodiment cannot involve an inventive step. The compositions of the present application do not show any surprising or unexpected effects in view of those of D2.
9. It appears that the subject-matter of present claims 2, 5, 7, 8, and 9 does not involve an inventive step since the application on file does not contain any indications, surprising effects or unexpected results by virtue of the distinguishing features in view of the cited prior art (Art. 33(3) PCT).
10. The subject-matter of present claims 1-10 satisfies the criterion set forth in Article 33 (4) PCT.

For the assessment of present claims 11 on the question whether it is industrially applicable, no unified criteria exist in the PCT Contracting States. Although said claim is characterized by unclear features it appears that according to its nature, it can be made or used (in the technological sense) in any kind of industry (PCT-Examination Guidelines, C-II, 4.12; Art. 33(1) and (4) PCT, Rule 5.1(a)(vi) PCT).

Re Item VI

Certain documents cited

**INTERNATIONAL PRELIMINARY
EXAMINATION REPORT - SEPARATE SHEET**

International application No. PCT/EP00/00357

Certain published documents (Rule 70.10)

Application No Patent No	Publication date (day/month/year)	Filing date (day/month/year)	Priority date (valid claim) (day/month/year)
EP-A-0 902 076	17.03.1999	02.09.1998	12.09.1997

This document discloses electrical well logging in which carbon type fibres or flakes (see paragraphs [0033-0035]) are added to a non-conductive fluid.

Re Item VIII

Certain observations on the international application

1. Claim 11 is unclear because said claim does not describe an actual method (Art. 6 PCT; PCT Examination Guidelines C-III-3.1).
2. The feature "and the like" used in claim 11 is undefined and therefore unclear (Art. 6 PCT).
3. It appears that claim 11 expresses only a mere wish.

PATENT COOPERATION TREATY

PCT

INTERNATIONAL SEARCH REPORT

(PCT Article 18 and Rules 43 and 44)

Applicant's or agent's file reference 95.0114	FOR FURTHER ACTION see Notification of Transmittal of International Search Report (Form PCT/ISA/220) as well as, where applicable, item 5 below.	
International application No. PCT/EP 00/ 00357	International filing date (<i>day/month/year</i>) 13/01/2000	(Earliest) Priority Date (<i>day/month/year</i>) 16/01/1999
Applicant SOFITECH N.V. et al.		

This International Search Report has been prepared by this International Searching Authority and is transmitted to the applicant according to Article 18. A copy is being transmitted to the International Bureau.

This International Search Report consists of a total of 3 sheets.
☒ It is also accompanied by a copy of each prior art document cited in this report.

1. Basis of the report

- a. With regard to the **language**, the international search was carried out on the basis of the international application in the language in which it was filed, unless otherwise indicated under this item.

☐ the international search was carried out on the basis of a translation of the international application furnished to this Authority (Rule 23.1(b)).
- b. With regard to any **nucleotide and/or amino acid sequence** disclosed in the international application, the international search was carried out on the basis of the sequence listing :

☐ contained in the international application in written form.
☐ filed together with the international application in computer readable form.
☐ furnished subsequently to this Authority in written form.
☐ furnished subsequently to this Authority in computer readable form.
☐ the statement that the subsequently furnished written sequence listing does not go beyond the disclosure in the international application as filed has been furnished.
☐ the statement that the information recorded in computer readable form is identical to the written sequence listing has been furnished
2. ☐ **Certain claims were found unsearchable** (See Box I).
3. ☐ **Unity of invention is lacking** (see Box II).
4. With regard to the **title**,

☒ the text is approved as submitted by the applicant.
☐ the text has been established by this Authority to read as follows:
5. With regard to the **abstract**,

☒ the text is approved as submitted by the applicant.
☐ the text has been established, according to Rule 38.2(b), by this Authority as it appears in Box III. The applicant may, within one month from the date of mailing of this international search report, submit comments to this Authority.
6. The figure of the **drawings** to be published with the abstract is Figure No.

☐ as suggested by the applicant. ☒ None of the figures.
☐ because the applicant failed to suggest a figure.
☐ because this figure better characterizes the invention.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/JP 00/00357

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C09K7/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	CALLONI G. ET AL; "Carbon Black: A Low Cost Colloidal Additive for Controlling Gas-Migration in Cement Slurries"; SPE International Symposium on Oilfield Chemistry; San Antonio, Texas, USA; 14-17 February 1995; SPE 28959 XP000915655 page 146, column 2, paragraph 5 page 148, column 2, paragraph 2; tables 1,2	1-6, 10, 11
Y	----	1-11
Y	US 4 012 329 A (HAYES JOHN B ET AL) 15 March 1977 (1977-03-15) column 5, line 24 - line 35 ----- -/--	1-11

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

16 June 2000

Date of mailing of the international search report

06/07/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel: (+31-70) 340-2040, Tx: 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

olde Scheper, B

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/JP 00/00357

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4012329	A	15-03-1977	NONE	
US 4689161	A	25-08-1987	AT 76119 T	15-05-1992
			AU 593248 B	08-02-1990
			AU 5729186 A	27-11-1986
			BR 8602338 A	21-01-1987
			CA 1302029 A	02-06-1992
			DE 3685256 A	17-06-1992
			EP 0202940 A	26-11-1986
			JP 1633974 C	20-01-1992
			JP 2057837 B	06-12-1990
			JP 62030178 A	09-02-1987
			KR 9309246 B	24-09-1993
			US 4735733 A	05-04-1988
			US 4743431 A	10-05-1988
			ZA 8603570 A	26-08-1987
EP 0449257	A	02-10-1991	US 5068041 A	26-11-1991
			AT 154627 T	15-07-1997
			AU 638563 B	01-07-1993
			AU 7398191 A	03-10-1991
			CA 2039490 A	01-10-1991
			DE 69126558 D	24-07-1997
			DK 449257 T	29-12-1997
			EP 0764711 A	26-03-1997
			NO 176360 B	12-12-1994
			US 5869433 A	09-02-1999
			US 5189012 A	23-02-1993
			US H1000 H	03-12-1991
EP 0902076	A	17-03-1999	US 6006831 A	28-12-1999
			CA 2244409 A	12-03-1999
			NO 984150 A	15-03-1999

INTERNATIONAL SEARCH REPORT

International Application No

PC 00/00357

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4 689 161 A (BLUMENTHAL JACK L ET AL) 25 August 1987 (1987-08-25) column 1, line 42 - line 55 column 10, line 19 -column 11, line 36; figure 1; examples 10,11.14; tables 5,6,8-10	1-11
A	MARK, H.F. EDITOR: "Encyclopedia of Polymer Science and Engineering, Vol. 2, "Carbon Black", pages 623-637" 1985 , JOHN WILEY & SONS , NEW YORK XP002140365	1-11
Y	EP 0 449 257 A (MI DRILLING FLUIDS CO) 2 October 1991 (1991-10-02) page 4, line 13 - line 15	1-11
P,Y	EP 0 902 076 A (SOFITECH NV ;SCHLUMBERGER CIE DOWELL (FR)) 17 March 1999 (1999-03-17) the whole document	1-11

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification : Not classified	A2	(11) International Publication Number: WO 00/41480 (43) International Publication Date: 20 July 2000 (20.07.00)
(21) International Application Number: PCT/EP00/00357 (22) International Filing Date: 13 January 2000 (13.01.00) (30) Priority Data: 9900904.5 16 January 1999 (16.01.99) GB (71) Applicant (for all designated States except CA FR US): SOF-ITECH N.V. [BE/BE]; Rue de Stalle 142, B-1180 Brussels (BE). (71) Applicant (for CA only): SCHLUMBERGER CANADA LIMITED [CA/CA]; 24th Floor, Monenco Place, 801 6th Avenue, S.W., Calgary, Alberta T2P 3W2 (CA). (71) Applicant (for FR only): COMPAGNIE DES SERVICES DOWELL SCHLUMBERGER [FR/FR]; 50, avenue Jean-Jaurès, F-92541 Montrouge (FR). (72) Inventors; and (75) Inventors/Applicants (for US only): SAWDON, Christopher [GB/GB]; 6 Southview Road Biscovey, Par, Cornwall PL24 2HJ (GB). TEHRANI, Mostafa [GB/GB]; 41 Trenance Road, St. Austell, Cornwall PL25 5AL (GB). CRADDOCK, Paul [GB/GB]; 193 Creak-A-Vose Park, St Stephen, St Austell, Cornwall PL26 7ND (GB). LAWSON, Anthony		[GB/GB]; 7 Menabilly Road, St Austell, Cornwall PL25 4DY (GB). (74) Agent: MENES, Catherine; Etudes et Productions Schlumberger, Division Dowell, 26, rue de la Cavée, BP 202, F-92142 Clamart Cedex (FR). (81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: ELECTRICALLY CONDUCTIVE NON-AQUEOUS WELLBORE FLUIDS		
(57) Abstract A wellbore fluid having a non-aqueous continuous liquid phase that exhibits an electrical conductivity increased by a factor in order of 10^4 to 10^7 compared to conventional invert emulsion comprises from about 0.2 % to about 10 % by volume of carbon black particles, and one or more emulsifying surfactant(s) selected from the class including: nonionic emulsifiers of Hydrophilic-Lipophilic Balance (HLB) less than about 12, and anionic surfactants wherein the counter-ion (cation) is any of alkali metal, ammonium, or hydrogen ions. This wellbore fluid can be used for drilling or completing a well and can be used for providing enhanced information from electrical logging tools, measurement while drilling, logging while drilling, geosteering and the like.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Electrically Conductive Non-Aqueous Wellbore Fluids

This invention relates to non-aqueous wellbore fluids and in particular concerns wellbore fluids which are electrically conductive. The invention also relates to the use of said wellbore fluids for drilling or completing subterranean wells such as oil and gas wells.

In the process of rotary drilling a well, a drilling fluid or mud is circulated down the rotating drill pipe, through the bit, and up the annular space between the pipe and the formation or steel casing, to the surface. The drilling fluid performs different functions. It removes cuttings from the bottom of the hole to the surface, suspends cuttings and weighting material when the circulation is interrupted, controls subsurface pressure, isolates the fluids from the formation by providing sufficient hydrostatic pressure to prevent the ingress of formation fluids into the wellbore, cools and lubricates the drill string and bit, maximises penetration rate etc. An important objective in drilling a well is also to secure the maximum amount of information about the type of formations being penetrated and the type of fluids or gases in the formation. This information is obtained by analysing the cuttings and by electrical logging technology and by the use of various downhole logging techniques, including electrical measurements.

The required functions can be achieved by a wide range of fluids composed of various combinations of solids, liquids and gases and classified according to the constitution of the continuous phase mainly in two groupings : aqueous (water-based) drilling fluids, and non-aqueous (mineral oil or synthetic-base) drilling fluids, commonly called 'oil-based fluids'.

Water-based fluids constitute the most commonly used drilling fluid type. The aqueous phase is made of fresh water or, more often, of a brine. As discontinuous phases, they may contain gases, water-immiscible fluids such as diesel oil to form an oil-in-water emulsion, and solids including clays and weighting material such as barite. The properties are typically controlled by the addition of clay minerals, polymers and surfactants.

In drilling water-sensitive zones such as reactive shales, production formations or where bottom hole temperature conditions are severe or where corrosion is a major problem, oil-based drilling fluids are preferred. The continuous phase is a mineral or synthetic oil and commonly contains water or brine as discontinuous phase to form a water-in-oil emulsion or invert emulsion. The solid phase is essentially similar to that of water-based fluids and these fluids too contain several additives for the control of density, rheology and fluid loss. The invert emulsion is formed and stabilised with the aid of one or more specially selected emulsifiers.

- 2 -

Although oil-based drilling fluids are more expensive than water-based muds, it is on the basis of the added operational advantage and superior technical performance of the oil-based fluids that these are often used for the drilling operations.

An area where oil-based muds have been at a technical disadvantage, because of their very low electrical conductivity, is in electrical well-logging. Various logging and imaging operations are performed during the drilling operation, for example while drilling in the reservoir region of an oil/gas well in order to determine the type of formation and the material therein. Such information may be used to optimally locate the pay zone, i.e. where the reservoir is perforated in order to allow the inflow of hydrocarbons to the wellbore.

Some logging tools work on the basis of a resistivity contrast between the fluid in the wellbore (drilling fluid) and that already in the formation. These are known as resistivity logging tools. Briefly, alternating current flows through the formation between two electrodes. Thus, the fluids in the path of the electric current are the formation fluids and the fluid which has penetrated the formation by way of filtration. The filtercake and filtrate result from filtration of the mud over a permeable medium (such as formation rock) under differential pressure.

Another example where fluid conductivity plays an important part in the drilling operation is in directional drilling where signals produced at the drill assembly have to be transmitted through an electrically conductive medium to the control unit and/or mud telemetry unit further back on the drill string.

At present the use of resistivity logging tools is limited mainly to cases where a water-based drilling fluid is used for the drilling operation (the very low conductivity of the base-oil in the case of oil/synthetic-base muds precludes the use of resistivity tools in such fluids). Although the brine dispersed in the oil phase is electrically conductive, the discontinuous nature of the droplets prevents the flow of electricity. Indeed, the inability of these emulsions to conduct electricity (until a very high potential difference is applied) is used as a standard test of emulsion stability. To that extent it is worth bearing in mind that the electrical conductivity of the oil base is typically in the range 10^{-6} to $5 \times 10^{-2} \mu\text{S.m}^{-1}$ at a frequency of 1 kHz while an electrical conductivity of not less than $10 \mu\text{S.m}^{-1}$ and preferably of no less than $10^3 \mu\text{S.m}^{-1}$ is desirable for electrical logging operations. So there is a need to increase the electrical conductivity of the fluid by a factor in the order of 10^4 to 10^7 .

A few attempts to make oil-based drilling fluids electrically conductive for the purpose of electrical logging have been reported though none of them has been a commercial success. U.S. Patent No. 2,542,020, U.S. Patent No. 2,552,775, U.S. Patent No. 2,573,961, U.S. Patent No. 2,696,468 and U.S. Patent No. 2,739,120, all to Fischer, disclose soap-stabilised oil-based

- 3 -

fluids comprising an alkaline-earth metal base dissolved in up to 10% by weight water. Fischer claims to reduce the electrical resistivity to below 500 ohm-m which corresponds to an increase of conductivity to $\kappa > 2000 \mu\text{S m}^{-1}$. However, those fluids happen to be very sensitive to contaminants and greater amounts of water lead to unacceptable increase of the fluid loss. In essence these fluids relied on the residual or added water content to dissolve the salts/surfactants. Moreover, the continuous oil phase fails to exhibit any increase of its electrical conductivity and there is no reference to what happens to the filtrate which under optimum conditions is made up essentially of the continuous oil phase.

Twenty five years later, U.S. Patent 4, 012,329 disclosed an oil-external micro-emulsion made with sodium petroleum sulfonate and reported of resistivity $< 1 \text{ ohm-m}$ ($\kappa > 1 \text{ S m}^{-1}$). In such a micro-emulsion, the sodium petroleum sulfonate forms micelles that contain water and the clay so that the clay has to be added as a dispersion in water and cannot be added as dry powder. It should be also emphasised that a micro-emulsion is distinctly different from a standard emulsion, being thermodynamically stable, smaller in size, higher in surface to volume ratio and forming both filtercakes and fluid filtrate of a different nature. Obtaining the necessary combination of bulk properties and non-damaging rock interactions is more difficult than for a standard direct or invert emulsion fluid, and such fluids are not generally favoured for drilling oil wells.

Although the prior art contains formulations for making oil-based drilling fluid conductive, the methods so described adversely affect other mud properties, another reason why none have been successfully commercialised.

The aim of this invention is thus to provide a non-aqueous wellbore fluid which exhibits a substantial electrical conductivity.

When mixed in an article at sufficient concentrations, carbon black is known to impart electrical conductivity to otherwise insulating materials such as plastics or elastomers. The extremely small carbon black particles ($\ll 1 \text{ micron}$) are known to form an interconnecting network which allows the conduction of electricity. Such articles can thus, for instance, avoid the build up of static electricity or shield against electromagnetic interference.

However, when carbon black was added to a conventional invert emulsion oil-based drilling fluid or mud (hereinafter referred to as OBM), little or no useful increase in conductivity was observed.

More specifically it has been found that the calcium soaps of fatty acids such as tall oil fatty acid will interact with the network of carbon particles, decreasing the particle-particle attractive forces by adsorbing onto the particles. Similarly, invert emulsifiers or wetting agents having

- 4 -

primary, secondary, tertiary amine groups or quaternary ammonium groups have been found to adsorb similarly and disrupt the conductive network of carbon black particles. Examples of such amine-containing products include fatty alkyl amidoamines, fatty alkyl imidazolines, fatty alkylamidoamines further reacted or cross-linked with di- or tri-basic acids such as maleic acid. Such calcium fatty acid soaps and amine-functional products are in very common use in all invert emulsion drilling fluids known to the applicants.

This invention has discovered that when carbon black is mixed in an OBM containing certain types of emulsifiers and oil-wetting agents, high levels of electrical conductivity can be obtained at advantageously low concentrations of carbon black.

Surprisingly, it has been found that in spite of the very high surface area and adsorption capacity of carbon black, certain invert emulsifiers and oil-wetting agent types do not disrupt the electrically conductive carbon black network.

In accordance with the invention, an electrically conductive invert emulsion wellbore fluid comprises from about 0.2% to about 10% by volume of carbon black particles and one or more emulsifying surfactant(s) selected from the class including: nonionic emulsifiers of Hydrophilic-Lipophilic Balance (HLB) less than about 12, and anionic surfactants wherein the counter-ion (cation) is any of alkali metal, ammonium, or hydrogen ions

All non-ionic surfactants found to date of an Hydrophilic-Lipophilic Balance (HLB) suitable to promote invert emulsification, do not destroy the conductivity. These include the diethanolamides based on higher fatty acids of more than 12 carbon atoms such as oleic acid or tall oil fatty acid (TOFA), alkoxylated higher fatty alcohols, alkoxylated alkylphenols, and ethylene oxide/propylene oxide block polymers. Generally, the more suitable HLB values are less than 10, but occasionally in combination with other emulsifiers, higher HLB values up to a maximum of 12 can be useful.

The other suitable classes of surfactants are anionic surfactants of sufficiently lipophilic character where the anionic surfactant is in the form of an alkali metal soap, the ammonium soap, or as the free acid. Polyvalent metal ion (e.g. calcium) soaps of these anionic surfactants are excluded because they have been found to disrupt the conductive network of carbon black particles, presumably by adsorption through ion-bridging by the polyvalent cation. The most preferred anionic surfactants are sulphonates such as alkane sulphonates, alpha-olefin sulphonates, alkylarene sulphonates, polyolefin sulphonates, and acyl taurates, all characterised by the carbon number of the hydrophobic moiety being at least about 12.

Other suitable anionic emulsifiers or wetting agents include the alkali metal or ammonium salts, or the free acid of fatty acids of 12 or more carbon atoms, phosphate esters of ethoxylated

alcohols of 12 or more carbon atoms, phosphate esters of ethoxylated alkylphenols of 14 or more carbon atoms, and alkylaminomethylene phosphonic acids wherein the alkylamine precursor contains 12 or more carbon atoms.

The total dose of emulsifiers is preferably in the range of 0.5% to 10%, based on the total weight of the wellbore fluid.

A preferred carbon black in this invention has a significantly higher specific surface area (i.e. at least 500 m²/g) than the conventional carbon black. A very suitable grade has a specific surface area of about 1500 m²/g compared to 100-300 m²/g of the conventional black. This gives the carbon black particles a higher ability to form an interconnecting network of particles which leads to a thixotropic rheological effect and a significant increase in conduction of electricity.

The most important attribute of this invention is that the electrical conductivity of the fluid is increased by a factor of the order of 10⁴ to 10⁷. This allows the successful application of many electrical logging techniques and the transmission of electrical telemetry signals when organic liquid-based wellbore fluids fill the borehole. Another object of the present invention is therefore a method of providing enhanced information from electrical logging tools, measurement-while-drilling (MWD), logging-while-drilling (LWD), geosteering and the like wherein the efficiency is enhanced by the improved electrical conductivity wellbore fluids of the invention.

In this invention it has been found that electrically conductive, oil-based drilling fluids can be provided which maintain the performance advantages expected from known oil-based (or synthetic organic liquid-based) drilling fluids. Therefore, the fluids of this invention minimise adverse interactions with drilled rock formation, such as clay formation swelling or dispersion, hole collapse, or the undesirable dissolution of underground salt formations. They also provide the performance advantages expected from oil-based fluids with regard to enhanced lubricity, reduced differential sticking of drill pipe, and good stability at high temperatures.

According to a preferred embodiment of the present invention, the wellbore fluid also comprises material capable of precipitating or complexing polyvalent metal cations such as the ions of calcium, magnesium and iron which may contaminate the wellbore fluid. This is to prevent the metal cation from forming a soap with emulsifiers which then adsorbs on the surface of carbon black particles and interferes with the conductive network.

Examples of precipitating materials are dissolved anions such as phosphate, carbonate or silicate. Examples of suitable complexing agents are the alkali metal or ammonium salts, or the free acids, of citric acid, gluconic acid, glucoheptanoic acid, ascorbic acid, erythorbic acid, nitrolotriacetic acid, ethylene diamine tetraacetic acid, diethylenetriamine pentaacetic acid,

- 6 -

hydroxyethylidene diphosphonic acid, nitrolotrismethylenephosphonic acid, aminomethylene phosphonates based on ethylene diamine or diethylene triamine or higher ethyleneamines, and polyphosphates such as tetrasodium pyrophosphate

The continuous non aqueous phase may be selected from any refined or synthetic fluid known to be suitable as a wellbore fluid base liquid such as crude oil, hydrocarbon refined fractions from crude oil such as diesel fuel or mineral oil, synthetic hydrocarbons such as *n*-paraffins, alpha-olefins, internal olefins, and poly-alphaolefins; synthetic liquids such as dialkyl ethers, alkyl alkanoate esters, acetals; and natural oils such as triglycerides including rape-seed oil, sunflower oil and mixtures thereof. Low toxicity and highly biodegradable oils will be generally preferred especially for offshore drilling.

The discontinuous liquid phase is water or a brine and is present from about 0.5% to about 70% by volume of the emulsion.

In order to provide other properties required from wellbore fluids, the wellbore fluids of this invention may further contain any known wellbore fluid additives such as clay, organoclay, or polymeric viscosifiers, filtration reducers such as lignite derivatives or powdered gilsonite filtration reducers, asphalts, asphaltites or polymers swollen by the oil, weighting agents such as finely divided barytes or hematite, lubricating additives, or any other functional additive known to those skilled in the art. These additives aim to provide a drilling mud that has the following characteristics :

- be fluid and produce affordable pressure drop in surface pipes and drill string
- have a yield stress suitable for supporting/transporting mud solids and drill cuttings
- be chemically, thermally and mechanically stable
- provide hole stability
- provide good lubricity
- prevent excessive fluid loss to the formation

The invention will now be illustrated by the following examples.

Example 1.

This example demonstrates the effectiveness of carbon black in increasing the electrical conductivity of a non-conductive mineral oil (Surdyne B140). The conductivity of the oil is below 1 $\mu\text{S/m}$.

We prepared a 1.5% by weight dispersion of carbon black in the mineral oil. The carbon black particles form irregular-shaped aggregates of extremely fine carbon particles fused together.

- 7 -

The size of the aggregates is in the range 10-250 nm but the larger aggregates may be reduced in size by mechanical shearing. The conductivity of the oil-carbon black dispersion was about 20000 $\mu\text{S/m}$ at 500Hz and at room temperature.

Example 2.

In this example we show the effect of carbon black addition on the conductivity of an oil-based mud using a conventional tall oil fatty acid calcium soap as the emulsifier:

Table1. Formulation for a weighted mud with conventional fatty acid invert emulsifier:
oil/water ratio:80/20.

Components	Amount in 350ml of mud
Mineral oil (Surdyne B140)	183.3 g
Tall oil fatty acid	9.0 g
Fluid loss additive (TRUFLO 100™)	4.5 g
Lime	5.0 g
Carbon black	6.0 g
Sodium chloride	22.67 g
Water	63.2 g
Barite	131.2 g

The conductivity of the full mud formulation is reduced to about 15 $\mu\text{S/m}$ at 500Hz. The results suggest that a conventional soap of tall oil fatty acid emulsifier (as used in almost all conventional oil-based mud formulations) does not allow the conductive network of carbon black particles to form. This is ascribed to strong adsorption of the calcium neutralised emulsifier on the carbon black particles, inhibiting the particle-particle interactions which form the network.

Example 3.

Effect of carbon black on the electrical conductivity of an oil-based mud which uses fatty acid diethanolamides (WITCAMIDE 511, a product of WITCO) as the emulsifier:

Table 2. Formulation for a weighted conductive OBM: oil/water ratio: 80/20

Components	Amount for 350ml of mud
Mineral Oil (Surdyne B 140)	182.3 g
Non-ionic emulsifier	8.0 g
Alpha-olefin sulphonate emulsifier	1.0 g
Fluid loss additive (TRUFLO 100™)	4.5 g
Carbon black	6.0 g
NaCl	21.43 g
Water	59.75 g
Barite	131.1 g

The conductivity of the above formulation was 10,000 $\mu\text{S/m}$ at 500Hz in the full mud formulation. It can be seen that this emulsifier type allows the carbon black conductive network (and hence conductivity) to be maintained, whilst imparting good emulsion stability, even in a weighting fluid where the barite has a diluting effect on the conductive network and reduces the conductivity to some extent. The function of the alpha-olefin sulphonate in the formulation is to improve the oil-wetting of barite.

CLAIMS

1. An electrically conductive invert emulsion wellbore fluid comprising:-
 - i) from about 0.2% to about 10% by volume of carbon black particles, and
 - ii) one or more emulsifying surfactant(s) selected from the class including: nonionic emulsifiers of Hydrophilic-Lipophilic Balance (HLB) less than about 12, and anionic surfactants wherein the counter-ion (cation) is any of alkali metal, ammonium, or hydrogen ions.
2. A wellbore fluid according to Claim 1 wherein the carbon black exhibits a specific surface area of at least 500 m²/g, and preferably of at least 1500 m²/g.
3. A wellbore fluid according to any preceding Claim wherein the nonionic emulsifier(s) is (are) selected from the class including: diethanolamides based on fatty acids of more than 12 carbon atoms, alkoxyated fatty alcohols, alkoxyated alkylphenols, and ethylene oxide propylene oxide block polymers.
4. A wellbore fluid according to any preceding Claim wherein the anionic surfactant(s) is (are) selected from the class including: alkane sulphonates, alpha olefin sulphonates, alkyl arene sulphonates, polyolefin sulphonates and acyl taurates, all characterised by the carbon number of the hydrophobic moiety being at least about 12, and by the counter-ion (cation) being any of alkali metal, ammonium, or hydrogen ions.
5. A wellbore fluid according to any one of Claims 1 to 4 wherein the anionic surfactant(s) is (are) selected from the class including: fatty acids of 12 or more carbon atoms, phosphate esters of ethoxylated alcohols of 12 or more carbon atoms, phosphate esters of ethoxylated alkyl phenols of 14 or more carbon atoms, and alkyl aminomethylene phosphonates wherein the alkylamine precursor contains 12 or more carbon atoms, all characterised by the counter-ion (cation) being any of alkali metal ion, ammonium, or hydrogen ions.
6. A wellbore fluid according to any preceding Claim in which the total dose of emulsifier(s) is in the range 0.5% to 10% by weight.
7. A wellbore fluid according to any preceding Claim containing any material capable of precipitating or complexing polyvalent metal cations such as the ions of calcium, magnesium and iron.

- 10 -

8. A wellbore fluid according to Claim 8 wherein the emulsified brine phase contains dissolved anions such as phosphate, carbonate, silicate which will form insoluble precipitates with any ions of calcium, magnesium or iron cations.
9. A wellbore fluid according to Claim 8 wherein the complexing agent is selected from the class including the alkali metal or ammonium salts, or the free acids, of citric acid, gluconic acid, glucoheptanoic acid, ascorbic acid, erythorbic acid, nitrolotriacetic acid, ethylene diamine tetraacetic acid, diethylenetriamine pentaacetic acid, hydroxyethylidene diphosphonic acid, nitrolotrismethylenephosphonic acid, aminomethylene phosphonates based on ethylene diamine or diethylene triamine or higher ethyleneamines, and polyphosphates such as tetrasodium pyrophosphate.
10. A method of drilling or completing a well wherein the wellbore fluid used is as in any preceding Claim.
11. A method of providing enhanced information from electrical logging tools, measurement-while-drilling (MWD), logging-while-drilling (LWD), geosteering and the like wherein the efficiency is enhanced by the improved electrical conductivity of any of the wellbore fluids as in Claims 1 to 9.



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁷: C09K 7/06	A3	(11) International Publication Number: WO 00/41480 (43) International Publication Date: 20 July 2000 (20.07.00)
(21) International Application Number: PCT/EP00/00357 (22) International Filing Date: 13 January 2000 (13.01.00) (30) Priority Data: 9900904.5 16 January 1999 (16.01.99) GB (71) Applicant (for all designated States except CA FR US): SOF-ITECH N.V. [BE/BE]; Rue de Stalle 142, B-1180 Brussels (BE). (71) Applicant (for CA only): SCHLUMBERGER CANADA LIMITED [CA/CA]; 24th Floor, Monenco Place, 801 6th Avenue, S.W., Calgary, Alberta T2P 3W2 (CA). (71) Applicant (for FR only): COMPAGNIE DES SERVICES DOWELL SCHLUMBERGER [FR/FR]; 50, avenue Jean-Jaurès, F-92541 Montrouge (FR). (72) Inventors; and (75) Inventors/Applicants (for US only): SAWDON, Christopher [GB/GB]; 6 Southview Road Biscovey, Par, Cornwall PL24 2HJ (GB). TEHRANI, Mostafa [GB/GB]; 41 Trenance Road, St. Austell, Cornwall PL25 5AL (GB). CRADDOCK, Paul [GB/GB]; 193 Creak-A-Vose Park, St Stephen, St Austell, Cornwall PL26 7ND (GB). LAWSON, Anthony		[GB/GB]; 7 Menabilly Road, St Austell, Cornwall PL25 4DY (GB). (74) Agent: MENES, Catherine; Etudes et Productions Schlumberger, Division Dowell, 26, rue de la Cavée, BP 202, F-92142 Clamart Cedex (FR). (81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> (88) Date of publication of the international search report: 28 September 2000 (28.09.00)
(54) Title: ELECTRICALLY CONDUCTIVE NON-AQUEOUS WELLBORE FLUIDS (57) Abstract <p>A wellbore fluid having a non-aqueous continuous liquid phase that exhibits an electrical conductivity increased by a factor in order of 10^4 to 10^7 compared to conventional invert emulsion comprises from about 0.2 % to about 10 % by volume of carbon black particles, and one or more emulsifying surfactant(s) selected from the class including: nonionic emulsifiers of Hydrophilic-Lipophilic Balance (HLB) less than about 12, and anionic surfactants wherein the counter-ion (cation) is any of alkali metal, ammonium, or hydrogen ions. This wellbore fluid can be used for drilling or completing a well and can be used for providing enhanced information from electrical logging tools, measurement while drilling, logging while drilling, geosteering and the like.</p>		